

SPEEDFIX

PROPERTIES

SPEEDFIX is a **bi-component resin mortar** made from **vinylester**, and is beige in color.

SPEEDFIX is a multi-action product effective for **bonding, sealing, repairing, and filling**. It is compatible with most construction materials (solid brick, concrete, lightweight concrete, stone, etc.)

The **CSTB's technical approval** covers the sealing of **reinforcing rods 8 to 25 mm wide**.


The **exceptional** anchoring qualities of **SPEEDFIX** (torsion and stripping) provide support for loads up to **930 Kg** in 25 MPa concrete.

SPEEDFIX can be applied to **damp surfaces** and at temperatures between **-5°C and 35°C**.

The cartridge can be resealed with its original stopper, and is **reusable** with a simple change of the mixing nozzle. **SPEEDFIX** produces **very little odor** and can be **used on interior surfaces**.

Does not contain styrene.

After drying, **SPEEDFIX** can withstand temperatures of **-40°C to 80°C** (for brief periods up to 110°C).

CE 0679
PERIMETRE
13

SPEEDFIX ETA-13/0728 ETAG 01-05 Option 7 M8 - M24 / rebar Ø 8 to 25mm
Option 1 M12-M16 European Technical Approval - Option 7 for non-cracked concrete Option 1 for cracked concrete

Product strictly for professional use.

Safety Sheet available on our website www.perimetre-sa.com in the "Products" (Produits) section.

This technical data sheet supersedes all previous versions concerning this product.

All information contained in this leaflet is based upon data considered to be true and accurate, based on laboratory tests, and is offered solely for the user's consideration. However, no guarantee or warranty of any kind, express or implied, is made with respect to the information contained herein. We cannot assume responsibility for the results obtained by others over whose methods we have no control. The user is responsible for assuring their suitability for a specific use, as well as the proper handling and application of the product. Our warranty does not extend beyond the replacement of a product that is proven defective within one year of its delivery. 11/07/2013

APPLICATION

Read the document listing the **product's technical characteristics** (available on the **PERIMETRE website** or by calling **+33 5.46.31.02.69**).

The cartridge can be used with the **PISTOCIM** caulking gun or with the mastic cartridge gun using a mixing nozzle from **PERIMETRE**.

Important: Holes must not contain stagnant water and must be completely dust-free.

Test the product on natural stone and marble to verify whether it causes any discoloration.

For more information, please refer to the instruction leaflet.

Storage:

Store in a cool, dark, dry place in temperatures between 5°C and 25°C. Under these conditions, the cartridges can be stored for 18 months.

SAFETY INSTRUCTIONS

Contains dibenzoyl peroxide

R43: May cause sensitization by skin contact

R52/53: Harmful to aquatic organisms; may cause long-term adverse effects in the aquatic environment.

Keep out of the reach of children.

S3/7: Keep container tightly closed and keep in a cool place.

S14: Keep away from dirt, rust, alkali, acids and accelerants.

S24/25: Avoid contact with skin and eyes.

S36/37/39: Wear suitable protective clothing such as safety gloves and protection for the eyes and face.

S46: If swallowed, seek medical advice immediately and show this container or label.

S61: Avoid release into the environment. Refer to special instructions and / or safety data sheet.